

CLIENT: Onyx Collection Inc.
202 Anderson
Belvue, KS 66407

Test Report No: TJ2009-3 Rev. 3

Date: July 8, 2016

REFERENCE: Testing was originally reported under SGS Test Report Number 654:009918 issued on 1/28/2008. The testing was performed under the same International Accreditation Service ISO 17025 accreditation number TL-282.

REVISION: Revision to QAI Laboratories test report number TJ2009-Rev. 2 issued on Jun 6, 2014 to include a compliance statement to ANSI Z124.2.

SAMPLE ID: Two shower bases identified by client as, "STD Cappuchino 616136 and STD Adobe 616135", were received in good condition on 1/14/08. This report also applies to sizes listed in Table 1.

SAMPLING DETAIL: Test samples were submitted to the laboratory directly by the client. No special sampling conditions or sample preparation were observed by QAI.

DATE OF RECEIPT: Samples were received at QAI on 1/14/08

TESTING PERIOD: 1/15/08 – 1/28/08

AUTHORIZATION: Signed Work Order by John McCarthy

TEST PROCEDURE: The units were evaluated in accordance with ANSI Z124.1.2-2005 and ANSI Z124.2-1995. No revisions to this report will be allowed after 90 days of the report date.

TEST RESULTS: The units, and those listed in Table 1, do comply with all the requirements of ANSI Z124.1.2-2005 and ANSI Z124.2-1995.

PREPARED BY

**SIGNED FOR AND ON BEHALF OF
QAI LABORATORIES, INC.**



Joe Cavett
Plumbing Project Manager



J. Brian McDonald
Operations Manager

Table 1

32" X 32"	48" X 30"	60" X 32" Left offset drain
36" X 32"	48" X 32"	60" X 32" Right offset drain
36" X 36"	48" X 33-1/2"	60" X 34"
36" X 36" with curb on two sides	48" X 36"	60" X 36"
36" X 42"	48" X 42"	60" X 42"
36" X 48"	48" X 48"	36" Neo Angle
42" X 32"	54" X 36"	38" Neo Angle
42" X 34"	60" X 30"	42" Neo Angle
42" X 36"	60" X 30" Left offset drain	48" Neo Angle
42" X 42"	60" X 30" Right offset drain	54" Neo Angle
42" X 48"	60" X 32"	60" Neo Angle

Test Procedure and Results

I. ANSI Z124.1.2-2005

2.1 Material:

Pass

Material: Solid Surface / Cultured Marble
 Type: II
 Color: Tan

2.1.3 Supporting Structure

NA

2.2 Dimensional Tolerances:

Reference

Model: STD Cappuchino 616136

<u>Dimension</u>	<u>Measured</u>	<u>Manufacturer's Stated Dimensions</u>
Length, in.:	<u>59-15/16"</u>	<u>60"</u>
Width, in.:	<u>41-5/8"</u>	<u>42"</u>
Height, in.:	<u>4"</u>	<u>Not Stated</u>

Model: STD Adobe 616135

<u>Dimension</u>	<u>Measured</u>	<u>Manufacturer's Stated Dimensions</u>
Length, in.:	<u>31-5/8"</u>	<u>32"</u>
Width, in.:	<u>31-1/2"</u>	<u>32"</u>
Height, in.:	<u>4"</u>	<u>Not Stated</u>

THIS REPORT IS THE CONFIDENTIAL PROPERTY OF THE CLIENT ADDRESSED. THE REPORT MAY ONLY BE REPRODUCED IN FULL. PUBLICATION OF EXTRACTS FROM THIS REPORT IS NOT PERMITTED WITHOUT WRITTEN APPROVAL FROM QAI. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED FOR THE INDIVIDUAL PROJECT FILE REFERENCED. THE RESULTS OF THIS REPORT PERTAIN ONLY TO THE SPECIFIC SAMPLE(S) EVALUATED.

2.3	<u>Test Unit:</u>	Reference
	Unit Style: <u>Shower Pan Unit</u>	
	Model & Serial No.: <u>STD Cappuchino 616136</u>	
	Date of Mfg: -	
	Unit Style: <u>Shower Pan Unit</u>	
	Model & Serial No.: <u>STD Adobe 616135</u>	
	Date of Mfg: -	
	The units were installed in a test stand in accordance with the manufacturer's published instructions.	
2.4.	<u>Installation Instructions:</u>	Pass
	A copy of the manufacturer's installation instructions were supplied with the unit.	
2.5.	<u>Care and Maintenance Instructions:</u>	Pass
	A copy of the manufacturer's care and maintenance instructions were supplied with the unit.	
2.6.	<u>Identification:</u>	Pass
	Manufacturer's name or trademark: <u>Onyx</u>	
	2.6.1	NA
	<u>Field Flange Kits:</u>	
2.7	<u>Grab Bars:</u>	NA
2.8	<u>Raised Flanges and Tiling Beads:</u>	Pass
	Flange Height, in.: <u>1"</u> (1", Min – Shower Base)	
	Flange is integral with shower base	

3.0 WORKMANSHIP AND FINISH

3.3 Surface Tests:

Pass

	<u>3" dia.</u>	<u>Below Tub Rim</u>	<u>Wall Surround</u>
Major Cracks	<u>0 (0)</u>	<u>0 (0)</u>	<u>0 (0)</u>
Minor Cracks	<u>0 (0)</u>	<u>0 (0)</u>	<u>0 (0)</u>
Blisters	<u>0 (0)</u>	<u>0 (0)</u>	<u>0 (0)</u>
Surface Porosity	<u>0 (0)</u>	<u>0 (0)</u>	<u>0 (0)</u>
Molding Irregularities	<u>0 (1)</u>	<u>0 (8)</u>	<u>0 (16)</u>
Pits & Pinholes	<u>0 (8)</u>	<u>0 (16)</u>	<u>0 (48)</u>
Pinholes & Small Specks	<u>0 (4)</u>	<u>0 (8)</u>	<u>0 (24)</u>
Medium Specks	<u>0 (2)</u>	<u>0 (4)</u>	<u>0 (12)</u>
Large Specks	<u>0 (0)</u>	<u>0 (0)</u>	<u>0 (0)</u>

3.4 Subsurface Tests:

Pass

	<u>Rim</u>	<u>Bottom</u>
Voids Larger than 1/16in.	<u>0 (0)</u>	<u>0 (0)</u>
Voids smaller than 1/16.	<u>0 (8)</u>	<u>0 (8)</u>

4.0 STRUCTURAL INTEGRITY

4.2 Drain Fitting Connection:

Pass

<u>50 lb. Load Position</u>	<u>Cracks (0)</u>
1	<u>0</u>
2	<u>0</u>
3	<u>0</u>

4.3 Point Impact Loads:

Pass

<u>Load Height, in.</u>	<u>Impact Point</u>	<u>Cracks (0)</u>
36	Bottom	<u>0</u>
36	Bottom	<u>0</u>
36	Bottom	<u>0</u>
36	Rim	<u>0</u>
36	Rim	<u>0</u>
36	Rim	<u>0</u>
24	Bottom Radius	<u>0</u>
24	Bottom Radius	<u>0</u>
24	Bottom Radius	<u>0</u>

THIS REPORT IS THE CONFIDENTIAL PROPERTY OF THE CLIENT ADDRESSED. THE REPORT MAY ONLY BE REPRODUCED IN FULL. PUBLICATION OF EXTRACTS FROM THIS REPORT IS NOT PERMITTED WITHOUT WRITTEN APPROVAL FROM QAI. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED FOR THE INDIVIDUAL PROJECT FILE REFERENCED. THE RESULTS OF THIS REPORT PERTAIN ONLY TO THE SPECIFIC SAMPLE(S) EVALUATED.

4.4 Load on Seats **NA**

4.5 Loads on Rim and Bottom: **Pass**

Model: STD Cappuchino 616136

<u>300 lb. Load Location</u>	<u>Loaded Deflection, in. (0.150 max.)</u>	<u>Residual Deflection, in. (0.008 max.)</u>	<u>Cracks (0)</u>
Bottom center	<u>0.0595</u>	<u>0.003</u>	<u>0</u>

Model: STD Adobe 616135

<u>300 lb. Load Location</u>	<u>Loaded Deflection, in. (0.150 max.)</u>	<u>Residual Deflection, in. (0.008 max.)</u>	<u>Cracks (0)</u>
Bottom center	<u>0.0470</u>	<u>0.001</u>	<u>0</u>

4.6 Area Impact Loads On Surrounds: **NA**

4.7 Loads on Wall Surrounds: **NA**

4.8 Radii Load Test: **Pass**

<u>Failure Location</u>	<u>Cracks (0)</u>	<u>Chips (0)</u>	<u>Voids (0)</u>
None	<u>0</u>	<u>0</u>	<u>0</u>

4.9 Loads on Unsupported Areas: **NA**

5.0 Physical Characteristics

5.1 Color Fastness: **Pass**

Specimen:	<u>1</u>	<u>2</u>	<u>3</u>
Color Change (0):	<u>0</u>	<u>0</u>	<u>0</u>

5.2 Stain Resistance: Pass

Reagent	Exposure Time	Covered Specimen Rating	Uncovered Specimen Rating
Black Crayon	16 hrs.	<u>1</u>	<u>1</u>
Black Liquid Shoe Polish	16 hrs.	<u>1</u>	<u>1</u>
Blue Washable Ink	16 hrs.	<u>1</u>	<u>1</u>
Gentian Violet Solution	16 hrs.	<u>1</u>	<u>1</u>
Lipstick	16 hrs.	<u>1</u>	<u>1</u>
Hair Dye	16 hrs.	<u>1</u>	<u>1</u>
Iodine, 1%	16 hrs.	<u>1</u>	<u>1</u>

Total Stain Resistance Rating (50 max.): 14

5.3 Cleanability & Wear: Pass

Specimen	% Reflectance Loss (5% max.)	% Reflectance Loss After Additional Cleaning (2% max.)	Thickness inch
1	<u>1.45</u>	<u>n/a</u>	<u>0.5500</u>
2	<u>1.65</u>	<u>n/a</u>	<u>0.6310</u>
3	<u>1.90</u>	<u>n/a</u>	<u>0.6340</u>

5.4 Cigarette Test: Pass

Specimen:	<u>1</u>	<u>2</u>	<u>3</u>
After Glow Time (0, max.)	0	0	0

5.5 Chemical Resistance: Pass

(all "Yes")

Reagent	Service-able	Repair-able	Reagent	Service-able	Repair-able
Naphtha	<u>yes</u>	<u>yes</u>	Citric Acid, 10%	<u>yes</u>	<u>yes</u>
Ethyl Alcohol	<u>yes</u>	<u>yes</u>	Urea, 6% (Urine)	<u>yes</u>	<u>yes</u>
Amyl Acetate	<u>yes</u>	<u>yes</u>	Hydrogen Peroxide, 3%	<u>yes</u>	<u>yes</u>
Ammonia, 10%	<u>yes</u>	<u>yes</u>	Phenol, 5% (Lysol)	<u>yes</u>	<u>yes</u>
Toluene	<u>yes</u>	<u>yes</u>	Lye, 1%-2% (Drano)	<u>yes</u>	<u>yes</u>
Ethyl Acetate	<u>yes</u>	<u>yes</u>	Sodium Hypochlorite	<u>yes</u>	<u>yes</u>
Acetone	<u>yes</u>	<u>yes</u>	(Chlorox)	<u>yes</u>	<u>yes</u>

5.6 Ignition Test Pass

First Test Specimen	1 st Burn Time, Sec.	2 nd Burn Time, Sec.
1	1	0
2	1	0
3	0	1
4	0	0
5	1	0

Requirement: Less than 30sec.

5.7 Thermal Shock Resistance: Pass
(250 cycles @50°F and 150°F @ 1gpm)

Results: No Cracks, Crazeing, Blistering, or Spalling

Requirement: (No cracks, crazeing, blistering, or spalling)

6.1 Water Resistance: Pass
(Each change: 4, maximum; Total Rating: 9, maximum)

Specimen	Color Change (4)	Blistering (4)	Surface Profile Change (4)	Cracks (4)	Loss of Gloss (4)	Total Rating (9)
1	0.0	0.0	0.0	0.0	0.0	0.0
2	0.0	0.0	0.0	0.0	0.0	0.0
3	0.0	0.0	0.0	0.0	0.0	0.0

6.2 Laboratory test for non-integral flange seal: NA

6.3 Resistance to fungi and bacteria growth: NA

6.4 Puncture resistance test: NA

*** END OF TEST REPORT ***